


Cove — Ultrafabrics

Speaking directly to the senses, **Cove** brings to life a beautifully micro-beaded texture highlighted by an impressively bold palette. Uniting meticulous artisanship and ground-breaking technology in an ingenious symbiosis, Cove delivers a uniquely refined matte finish and richly saturated colors beyond traditional polyurethane varieties. The futuristic tactile appeal and visually pleasing aesthetic will deliver fresh styling to any setting.



-
- Superior durability – industry-leading 14+ weeks hydrolysis results
 - Blended backcloth for expanded upholstery capabilities
 - 200,000 double rubs (Wyzenbeek), 200,000 rubs (Martindale)
 - Bleach cleanable (1:5 bleach/water solution)
 - SCS Indoor Advantage Gold Certification
 - Meets Health Care Without Harm’s Healthy Interiors Criteria V2.3

An intelligent solution – the Ultrafabrics family of performance fabrics highlights boundary-pushing innovation where looks, feel and performance matter.



Cove from Ultrafabrics

Application

Interior Upholstery

General Specifications

Composition:

100% Polycarbonate Polyurethane Surface
65% Polyester, 35% Rayon Backing

Weight:

Approx. 10.3 oz. Per Square Yard
Approx. 350 Grams Per Square Metre

Thickness:

Approx. 1.1 Millimetres

Width:

54 Inches / 137 Centimetres

Repeat:

None

Performance

Abrasion:

ASTM D4157 / 200,000 Double Rubs (Wyzenbeek)*
BS EN ISO 12947-2 / 200,000 Rubs (Martindale)*
*meets or exceeds

Hydrolysis:

14+ Weeks
ASTM D3690 Sect. 6.11 (Hydrolytic Stability)
ISO 1419 Method C (Accelerated Ageing)

Adhesion of Coating: ASTM D751

Tear Strength: ASTM D2261

Breaking Strength: ASTM D5034

Tensile Strength: BS EN ISO 1421

Colorfastness

Light Fastness: AATCC 16.3, 200 Hours, Grade 4
ISO 105 B02, Grade 6

Crocking: AATCC 8, Grade 4-5 Wet & Dry

Flammability Requirements

- ASTM E84 (Adhered) - Class A
- CA TB 117 - Pass
- FMVSS 302 & 95/28 Annex IV - Pass
- NFPA 260 - Class 1
- UFAC - Class 1

These fabrics, when treated and/or used with other compatible furniture components, have been shown to perform under the fire test conditions of:

- ASTM E84 (Unadhered)
- BS 5852 Source 0, 1 & 5 (Cig, Match & Crib 5)
- IMO FTPC Part 8

For more information on certifications and standards, sustainability, as well as cleaning and care instructions, please visit our website.

