

NASSIMI

Nassimi LLC T 212.643.8080
370 Seventh Avenue T 800.521.5208
Suite 1600 F 212.643.2626
New York, NY 10001 W www.nassimi.com

Product Specification Sheet

Pattern: Muse

Date: 3/12/2012

The Symphony Collection

General Specifications

Weight (linear yard)	32.0 oz
Width	54 "
Thickness	1.15 mm
Gauge	0.480
Emboss	
Surface Composition	PVC
Substrate Composition	100% Brushed Polyester Knit
Substrate Weight	4.4 oz

General Treatments

UV Resistance	650 Hours	AATCC Test Method 16-2004, Option 3
Cold Crack	-20° F	CFFA-6 Federal Standard No. 191A-Method 5874
Mildew Resistant	Yes	CFFA-120 / ASTM G21-96
Anti-Bacterial	Yes	CFFA-300 / AATCC* Test Method 147-1998
Anti-Microbial	Yes	CFFA-120 / ASTM G21-96
Resilience ^{SR}	Yes	
Bleach Resistant	Yes	10% Dilution

Physical Strength Properties

Abrasion	500,000+	Double Rubs	CFFA-1A / Method ASTM D 4157-10 ACT STANDARD COTTONDUCK
Tear Strength	8.5 Warp	6.5 Fill	CFFA-16 / ASTM D2261-07a
Breaking Strength	131 Warp	95 Fill	CFFA-17 / ASTM D751-06
Seam Strength Tack Tear	60 Warp	40 Fill	CFFA-14 / Method ASTM D751-06
Crocking	5 Dry	5 Wet	AATCC-Method 8-2007
Flex Testing of Finish	25,000 Warp	25,000 Fill	CFFA-10 / ASTM D2097-03(2005)
Coating Adhesion	8.97 Warp	Full Bond Fill	ASTM D751-06

Flame Retardancy Standards

California Technical Bulletin 117, Section E	Pass	IMO A.652(16)8.2	Pass
UFAC Class I	Pass	IMO A.652(16)8.3	Pass
BIFMA CS-191-53, Section 3	Pass	ASTM E84 Adhered and Unadhered	Class I or A
MVSS 302	Pass		
NFPA 260	Pass		